

TECHNICAL DATA SHEET

TEST	REFERENCE	UNITS	AVERAGE RESULTS
MINIMUM BREAKING STRENGTH	EN 60811	Kn	292,52
ELONGATION	EN 60811	Gpa	200,6
THICKNESS OF INSULATION(av.)		mm	1,4
INNER DIAMETER		mm	15,70
OUTER DIAMETER		mm	18,50
MASS OF ROPE		kg/km	1278,82
MASS OF INSULATION		kg/km	112
MASS OF GREASE		kg/km	42

CHEMICAL ANALYSE OF WIRE RODE						
ELEMENT	C%	Si%	Mn%	P%(max)	S%(max)	Cu%max
REQUIREMENTS	0,35-1,00	0,10-0,30	0,40-1,20	0,035	0,035	0,20